

Technical datasheet for: epsotech PE CB1 HG

Overview and Structure

epsotech PE CB1 HG is a multi layer product with an innovative top layer, exhibiting excellent high gloss and scratch resistance.

Typical Physical Properties

Property	Value	Unit	Standard	Test Method
GENERAL PROPERTIES:				
Density*	0.92	g/cm ³	ISO 1183	-
MECHANICAL PROPERTIES:				
Tensile Modulus	1000	MPa	ISO 527	23°C 1mm/min
Yield stress	80	MPa	ISO 527	23°C 50mm/min
Elongation at Yield	-	%	ISO 527	23°C 50mm/min
Elongation at Break	>150	%	ISO 527	23°C 50mm/min
Charpy (notched)	NB	KJ/m ²	ISO 179	23°C, 1eA
Charpy (notched)	-	KJ/m ²	ISO 179	-30°C, 1eA
Charpy (un-notched)	-	-	-	-
Charpy (un-notched)	-	-	-	-
THERMAL PROPERTIES:				
VICAT Softening Point	-	°C	ISO 306	B/50
Heat Distortion Temperature	74	°C	-	B, 0.45MPa
UV STABILISATION:				
Stabilisation	-	-	-	
BURNING BEHAVIOUR:				
Burning Rate				
Flammability Rating				
Flammability Rating UL**	-	-	-	
SURFACE/VOLUME:				
MISCELLANEOUS:				
Mould Shrinkage	1.8 – 3.4	%	-	-
Thermoforming Temperature	130 - 200	°C	-	-

Unless otherwise stated, products are tested at a typical thickness of 4mm

* The density quoted should only be used as a guide. This value can change depending upon the type and quantity of pigments or additives used.

** Fire behaviour values given by raw material supplier or by indicative test on raw material. Not intended as a specification

Supplemental Information

Chemical Contact and cleaning

Reagent	Chemical resistance		Reagent	Chemical resistance
Acetone	Very good		Beer	Excellent
Acid – (Weak)	Excellent		Brake Fluid	Very good
Acid – (Strong)	Very good		Coffee	Excellent
Alcohol	Very good		Detergent	Excellent
Anti-freeze	Excellent		Diesel	Good
Base (Weak)	Excellent		Foodstuffs	Excellent
Base (Strong)	Good		Lubricating Oil	Good
Battery Acid	Very good		Petrol	Good

Chemical resistance is influenced by many factors, including concentration, temperature, exposure time and material stress. Therefore the data should only be used as a guide.

Most common mild soaps or detergents dissolved in warm water can be used to effectively clean general dirt and surface contaminants, but in all cases should be objectively tested. Abrasive products will damage the surface.

Storage and Drying

HDPE has a very low moisture absorption, therefore pre-drying is not normally required

Dimensional Tolerances

Standard tolerances are subject to the local standard tolerance set. Extra tolerance requirements may be possible on request and by special agreement

Disclaimer

Limited warranty and liability — Information in this document is believed to be accurate and reliable. However, epsotech and/or its subsidiaries do not give any representations or warranties, expressed or implied, as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. epsotech takes no responsibility for the content in this document if provided by an information source outside of epsotech. In no event shall epsotech be liable for any indirect, incidental, punitive, special or consequential damages (including - without limitation - lost profits, lost savings, business interruption, costs related to the removal or replacement of any products or rework charges) whether or not such damages are based on tort (including negligence), warranty, breach of contract or any other legal theory. Notwithstanding any damages that customer might incur for any reason whatsoever, aggregate and cumulative liability by epsotech towards customers for the products described herein shall be limited in accordance with the terms and conditions of commercial sale of epsotech

Right to make changes — epsotech reserves the right to make changes to information published in this document, including without limitation specifications and product descriptions, at any time and without notice. This document supersedes and replaces all information supplied prior to the publication hereof. The latest version of a published datasheet shall be available for download from the epsotech website, or the subsidiary websites of Carolex SAS and Axi-pack SAS, depending on the product range.

Suitability for use — epsotech sells thermoplastic sheet and monofilament products. Through commercial consultation, we offer material that may be suitable for customer requirements. However, the overall performance of an end product and suitability for use in any application, is not implied or warranted. Because of the large number of factors that influence our products during a customer's transformation process, customers should thoroughly evaluate, test and warranty their own parts for suitability and performance at end use.

Nothing in this document may be interpreted or construed as an acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.

Edition 1, May 2019.

Published by epsotech Holding GmbH, IM Reinfeld 2, Juelich Kirchberg, 52428 Germany